

## Technical Data Sheet PE WAX NV-204P

### Product Description:

Modulated wax NV-204P is used in refined low-density polyethylene cracking wax in the high-end field. It has high whiteness and high melting point, excellent thermal stability, excellent dispersion wetting, and excellent lubrication performance; its molecular weight is around 2500-3500, suitable for high-end mother batch and Excellent carrier of high-end metal pigments.

### technical parameter

quality index	appearance	Particle size (20mesh) %	viscosity (CPS@140°C)	density g/cm <sup>3</sup>	Shore hardness ShoreA	softening point °C	Thermal weightlessness (@200°C/2H) %
quality requirement	White powder	99	200 ± 50	0.93	95	110 ± 3	1

### Application Description

Application scope	Application suggestions	Product characteristics
Hot melt adhesive/adhesive	It is recommended to reduce viscosity by 20-30% and adjust polyolefins The setting time of EVA matrix.	Uniform molecular weight distribution and high softening point high viscosity Excellent heat resistance and thermal stability High hardness Excellent chemical resistance Good compatibility with other waxes Good lubrication performance Excellent pigment wettability Excellent dispersion performance
PVC (products/composite materials)	Suggest 0.5-1.5% as a metal mold release agent for PVC processing	
Color masterbatch	Suggest using 5-30% to improve the pigment in polyolefin matrix Dispersion "	
Thermoplastic road marking paint	To reduce the viscosity of hydrocarbon resin base, it is recommended to use 1-3%	
Plastic additives	It is recommended to use a 5-8% method to improve the performance of fillers Dispersion in polyolefin matrix "	
Waterproof roll material	Suggest adding 4-6% to improve the surface smoothness and hardness of the coating film	
Rubber products	Recommend 2-10% to improve processing performance and additive dispersion.	
Cable filling composite material	Suggest 5-10% to improve the performance of the moisture-proof layer.	
Other fields	Suggestions based on specific requirements	

## Packaging and Storage

**Product packaging:** 25kg/bag, standard packaging 1 ton/pallet

The product should be stored in a dry and dust-free location with a temperature below 50 °C, and protected from direct sunlight, away from sparks, and in a well ventilated area. It should be stored separately from oxidants and edible chemicals, and should not be mixed, as this may lead to quality degradation, color and odor changes, and may affect the physical properties of the product



**Please visit our website for more information:** [www.chemnovo.com.cn](http://www.chemnovo.com.cn) / [www.yihe911.com](http://www.yihe911.com)

上海毅和新材料科技有限公司

chemnovo®、novo®、科米诺® And other related trademark copyrights belong to Shanghai Yihe New Materials Co., Ltd (©Shanghai Yihe New Materials Co.,Ltd)