

## Technical Data Sheet PE WAX NV-408P

### Product Description:

NV-408P is a refined synthetic wax suitable for mid to high-end fields. It has excellent thermal stability, excellent dispersion flowability, and excellent lubrication performance. The product has good flowability, good heat resistance, high hardness, good paint hardness, scratch resistance, rolling resistance, and good temperature resistance. It is especially recommended for road marking paint for shock line. It has good wetting and dispersion effect on titanium dioxide powder, good external sliding performance, and good antifouling ability of paint film.

### technical parameter

quality index	appearance	Particle size (20mesh)%	viscosity (CPS@140°C)	density g/cm <sup>3</sup>	Shore hardness ShoreA	softening point °C	Thermal weightlessness (@200°C/2H) %
quality requirement	White powder /tablet	99	30	0.91	91	105± 3	5

### Application Description

Application scope	Application suggestions	Product characteristics
PVC (products/composite materials)	It is recommended to use 0.5~1.5% as a metal mold release agent for PVC processing.	Low viscosity Excellent heat resistance and thermal stability High hardness Excellent chemical resistance Good compatibility with other waxes Good lubrication performance Excellent pigment wettability Excellent dispersion performance
Color masterbatch	Suggest using 5-30% to improve the dispersion of pigments in polyolefin matrices	
Thermoplastic road marking paint	To reduce the viscosity of hydrocarbon resin base, it is recommended to use 1-3%	
Plastic additives	It is recommended to use a 5-8% method to improve the dispersion of fillers in polyolefin matrices.	
Rubber products	Recommend 2-10% to improve processing performance and additive dispersion.	
Cable filling composite material	Suggest 5-10% to improve the performance of the moisture-proof layer.	
Other fields	Suggestions based on specific requirements	

### Packaging and Storage

**Product packaging:** 25kg/bag, standard packaging 1 ton/pallet

The product should be stored in a dry and dust-free location with a temperature below 50 ° C, and protected from direct sunlight, away from sparks, and in a well ventilated area. It should be stored separately from oxidants and edible chemicals, and should not be mixed, as this may lead to quality degradation, color and odor changes, and may affect the physical properties of the product



**Please visit our website for more information:** [www.chemnovo.com.cn](http://www.chemnovo.com.cn) / [www.yihe911.com](http://www.yihe911.com)

©2019上海毅和新材料科技有限公司

chemnovo®, novo®, 科米诺® And other related trademark copyrights belong to Shanghai Yihe New Materials Co., Ltd (©Shanghai Yihe New Materials Co.,Ltd)